

TFI Report 441874-06

Testing of Resilient Floor Coverings

Customer

LG Hausys Ltd.
One IFC, 20 Yeouido-gong, Yeongdeungpo-gu
150-876 Seoul
SOUTH KOREA

Product

Resilient floor covering
DSW: DECOTILE 3.0T

Responsible at TFI

Katharina Keulen B. Sc.
Tel: +49 241 9679 151
k.keulen@tfi-online.de

This report includes 2 pages and 1 annex(es)

Aachen, 6 01 2015



Dr. Ernst Schröder

The present document is provided with a qualified electronic signature and is valid without autograph signature.

This report only applies to the tested specimens and has been established to the best of our knowledge. Only the entire report shall be reproduced. Under no circumstances, extracts shall be used. Furthermore, we apply the "General Terms and Conditions for the Execution of Contracts" of the Textiles & Flooring Institute GmbH, also with regard to the order execution.

1 Transaction

Test order	Residual indentation according to ISO 24343-1:2012
Order date	25 November 2014
Your reference	Dan Bi
Product designation	DSW: DECOTILE 3.0T
TFI sample number	14-11-0278

2 Product Specification

Use surface	PVC*
Construction	heterogeneous
Structure	flat
Pattern	multicoloured, unpatterned
Colour of the use surface	black, brown
Type of delivery	tiles
	*customer information

3 Results

Residual indentation [mm]	0.05
---------------------------	------

4 Annexes

Residual Indentation ^a	RED 441874-06
-----------------------------------	---------------

The annexes marked ^a are based on tests accredited in accordance with EN ISO/IEC 17025.

Annex RED - Residual Indentation

1 Transaction

Product designation DSW: DECOTILE 3.0T
TFI sample number 14-11-0278
Testing period 8 December 2014 -19 December 2014

2 Test Method / Requirements

ISO 24343-1:2012 Determination of indentation and residual indentation
Deviations None
The test was performed by an authorized subcontractor.

3 Results

Parameter	Result
Mean value for residual indentation [mm]	0.05
Mean value for the depth of indentation after 150 min. [mm]	0.25

Comments: none